



Knitted geocomposite from high tenacity PET yarns and nonwoven PET or PP geotextiles

Product designation			20/20	40/40	50/50	60/60	80/80	100/100
Tensile strength	MD	kN/m	25	45	55	70	90	110
	tolerance		-5	-5	-5	-10	-10	-10
<i>EN ISO 10319</i>	CMD	kN/m	25	45	55	70	90	110
	tolerance		-5	-5	-5	-10	-10	-10
Strain at nominal load	MD	%	9	9	9	9	9	9
	tolerance		± 4,5	± 4,5	± 4,5	± 4,5	± 4,5	± 4,5
<i>EN ISO 10319</i>	CMD	%	9	9	9	9	9	9
	tolerance		± 4,5	± 4,5	± 4,5	± 4,5	± 4,5	± 4,5
Mesh Size (standard)		mm	50x45	50x45	50x45	50x45	50x35	50x35
Form of supply			rolls					
Width (standard)			5					
Length (standard)			100					
Area		m ²	500					

Description

Armatex® RSR geocomposites are made by rashed technology – knitting. It is a fix connection of knitted geogrid made of high tenacity PET yarns and nonwoven PET or PP geotextile. Rolls can be placed on the open air and piled up max. into 5 layers. Keep out of reach fire! Rolls can be transported by truck, train or in containers.

Kordárna Company is capable of designing and manufacturing product precisely as per requirements. The values given are indicative and correspond to average results obtained in our laboratories and in testing institutes. The right is reserved to make changes without notice at any time.



Kordtrade, s.r.o.
 Velká nad Veličkou 890
 696 74 Czech Republic
www.kordarna.cz