

Geocomposite made from woven (PET) and nonwoven (PET or PP) geotextiles

Product designation			80/80	200/200
Tensile strength	MD	kN/m	90	220
tolerance			-10	-20
<i>EN ISO 10319</i>	CMD	kN/m	90	220
tolerance			-10	-20
Elongation at break	MD	%	21	21
tolerance			+/-6	+/-6
<i>EN ISO 10319</i>	CMD	%	16	21
tolerance			+/-6	+/-6
Form of supply			rolls	
Width (standard)		m	5	
Length (standard)		m	100	
Area		m ²	500	

Description Kortex[®] PEC is a geocomposite, made of high tenacity PET woven geotextile and PET or PP nonwoven geotextile. Rolls can be placed on the open air and piled up max. into 5 layers. Keep out of reach fire! Rolls can be transported by truck, train or in containers. Kordárna Company is capable of designing and manufacturing product precisely as per requirements.
The values given are indicative and correspond to average results obtained in our laboratories and in testing institutes. The right is reserved to make changes without notice at any time.



Kordtrade, s.r.o.
Velká nad Veličkou 890
696 74 Czech Republic

www.kordarna.cz